



Bepoxy



Tersertifikasi
Food Grade sesuai
U.S. FDA 21
CFR 175.300.



Jenis	Solvent Free
Penampilan	Kilap
Ketebalan	min 200 micron
Mixing Ratio	A : B = (4 : 1) Solid, (2 : 1) Clear
Daya Sebar Teoritis	4m ² /liter set per lapis ketebalan 200 micron
Kering Sentuh	6-8 jam, Recoating 16-24 jam
Waktu Kering	7 hari
Pengencer	5% thinner PU (jika diperlukan)
Umur Campuran	20 menit
Kemasan	0.8 kg Bepoxy A, 0.2 kg Bepoxy B
	0.6 kg Bepoxy A, 0.3 kg Bepoxy B (clear)
Cara Aplikasi	Kuas, spray dan roll

